

Lewatit® MonoPlus TP 260 is a weakly acidic, macroporous cation exchange resin with chelating amino methyl phosphonic acid groups designed for the selective removal of heavy metal cations and alkaline earth cations.

The monodisperse, uniform sized beads of **Lewatit® MonoPlus TP 260** are mechanically and osmotically more stable than ion exchange resin beds with heterodisperse bead size distribution. Additionally they offer superior kinetic behavior which leads to faster uptake of cations and a better utilization of capacity. Due to its modified polymer structure and substitution grade it is for example suitable for use in:

- fine polishing of brine fed to chloralkali membrane cells, e.g. by removal of Ca^{2+} , Mg^{2+} , Ba^{2+} , Sr^{2+} ; in the absence of Fe^{3+} ions
- fluoride (F) removal using aluminum (Al) doped **Lewatit® MonoPlus TP 260**
- antimony (Sb) and tungsten (Bi) removal from copper containing electrolyte
- uranium (U) removal from crude phosphoric acid
- titanium (Ti) removal from recycled battery acid
- aluminum (Al) removal from urea solutions
- lead (Pb) and strontium (Sr) removal from BF_4^- containing waste water out of PCB production
- removal of iron(II), nickel and zinc from 5 % gluconate containing liquid metal working

Heavy metal and alkaline earth cations are removed out of neutralized process and waste waters in following order (decreasing affinity):

Uranium (UO_2^{2+}) > Lead > Copper > Zinc > Nickel > Cadmium > Cobalt >> Calcium > Magnesium > Strontium > Barium >>> Sodium.

The special properties of this product can only be fully utilized if the technology and process used correspond to the current state-of-the-art. Further advice in this matter can be obtained from Lanxess, Business Unit Liquid Purification Technologies.

Common Description

Delivery form	Na ⁺
Functional group	Aminomethylphosphonic acid
Matrix	Styrenic
Structure	Macroporous
Appearance	Beige, opaque

Specified Data

Uniformity coefficient		max.	1.1
Mean bead size	d50	mm	0.63 (+/- 0.05)
Total capacity (H ⁺ form)		min. eq/L	2.4

Typical Physical and Chemical Properties

Bulk density for shipment	(+/- 5%)	g/L	720
Density		approx. g/mL	1.18
Water retention (delivery form)		approx. weight %	58-62
Volume change (Na ⁺ - H ⁺)		max. approx. %	-35
Stability pH range			0-14
Stability temperature range		°C	1-80
Storability temperature range		°C	-20 - +40

Operation

Operating temperature		max. °C	80
Operating pH range	during exhaustion		1-12
Bed depth for single column		min. mm	1000
Back wash bed expansion per m/h (20°C)		%	4
Specific pressure loss kPa*h/m ² (15°C)		kPa*h/m ² (15°C)	1.1
Max. pressure loss during operation		kPa	250
Specific flow rate		max. BV/h	5-25
Freeboard	during backwash	min. vol. %	100

Regeneration

HCl regeneration	concentration	approx. wt. %	4-10
HCl regeneration	quantity co-current	min. g/L resin	150
Regeneration contact time		min. minutes	20
Slow rinse at regeneration flow rate		min. BV	5
Fast rinse at service flow rate		min. BV	5

This document contains important information and must be read in its entirety.

Conditioning

NaOH conditioning	concentration	approx. wt. %	4
NaOH conditioning, di-Na ⁺	quantity	min. g/l resin	80-96
Conditioning contact time		min. minutes	20
Slow rinse	at conditioning flow rate	min. BV	5
Fast rinse	at service flow rate	min. BV	5

This document contains important information
and must be read in its entirety.

Additional Information & Regulations

Safety precautions

Strong oxidants, e.g. nitric acid, can cause violent reactions if they come into contact with ion exchange resins.

Toxicity

The safety data sheet must be observed. It contains additional data on product description, transport, storage, handling, safety and ecology.

Disposal

In the European Community ion exchange resins have to be disposed, according to the European waste nomenclature which can be accessed on the internet-site of the European Union.

Storage

It is recommended to store ion exchange resins at temperatures above the freezing point of water under roof in dry conditions without exposure to direct sunlight. If resin should become frozen, it should not be mechanically handled and left to thaw out gradually at ambient temperature. It must be completely thawed before handling or use. No attempt should be made to accelerate the thawing process.

Packaging

The experience has shown that the packaging stability for reliable resin containment is limited to 24 months under the storage conditions described above. It is therefore recommended to use the product within this time frame; otherwise the packaging condition should be checked regularly.

This information and our technical advice – whether verbal, in writing or by way of trials – are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to check its validity and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sale and Delivery.

LANXESS Deutschland GmbH
Liquid Purification Technologies
Kennedyplatz 1
50569 Koeln
Germany

+49-221-8885-0
lewatit@lanxess.com

www.lanxess.com
www.lpt.lanxess.com

This document contains important information
and must be read in its entirety.